



[Document Name] Specification

[Title of the Invention] DIFFRACTION GRATING ELEMENT.

[Claims]

[Claim 1] A diffraction grating element characterized
5 in that:

in a transparent flat plate having a first surface and
a second surface that are parallel with one another and are
in contact with a medium, a diffraction grating is provided
on the first surface or within the transparent flat plate in
10 parallel with the first surface; and

at any temperature within a temperature range -20°C to
 $+80^{\circ}\text{C}$, a linear expansion coefficient of a period of the
diffraction grating, and a temperature coefficient of a
refractive index of the medium is 0.

15 [Claim 2] The diffraction grating element according to
claim 1, wherein:

the medium is air; and

the linear expansion coefficient of the period of the
diffraction grating is from $0.63 \times 10^{-6}/\text{K}$ to $1.23 \times 10^{-6}/\text{K}$.

20 [Claim 3] A diffraction grating element characterized
in that:

in a transparent flat plate having a first surface and
a second surface that are parallel with one another and are
in contact with a medium, a diffraction grating is provided
25 on the first surface or within the transparent flat plate in
parallel with the first surface;

the medium is air; and

a linear expansion coefficient of a period of the diffraction grating is from $0.65 \times 10^{-6}/K$ to $1.11 \times 10^{-6}/K$.

[Claim 4] A diffraction grating element characterized
5 in that:

in a transparent flat plate having a first surface and a second surface that are parallel with one another, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first
10 surface;

the transparent flat plate is disposed in a hermetically sealed gas or in a vacuum; and

a linear expansion coefficient of a period of the diffraction grating is $2.4 \times 10^{-7}/K$ or less.

[Claim 5] A diffraction grating element characterized
15 in that:

in a transparent flat plate having a first surface and a second surface that are parallel with one another and are in contact with a medium, a diffraction grating is provided
20 on the first surface or within the transparent flat plate in parallel with the first surface;

the medium is air; and

a linear expansion coefficient of a period of the diffraction grating is from $0.80 \times 10^{-6}/K$ to $0.95 \times 10^{-6}/K$.

[Claim 6] A diffraction grating element characterized
25 in that:

in a transparent flat plate having a first surface and a second surface that are parallel with one another, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface;

the transparent flat plate is disposed in a hermetically sealed gas or in a vacuum; and

a linear expansion coefficient of a period of the diffraction grating is $1.2 \times 10^{-7}/K$ or less.

[Claim 7] The diffraction grating element according to any one of claims 1, 3, and 5, wherein the transparent flat plate is made of silica glass to which an impurity has been added.

[Claim 8] The diffraction grating element according to any one of claims 1, 4 and 6, wherein the transparent flat plate is made of silica glass or crystallized glass to which an impurity has been added.

[Claim 9] The diffraction grating element according to any one of claims 1, 3, 4, 5, and 6, wherein the transparent flat plate is constituted by laminating a plurality of optical glasses with different linear expansion coefficients.

[Claim 10] The diffraction grating element according to any one of claims 1, 3, and 5, wherein the transparent flat plate is made of silica glass to which an impurity has been added at a different concentration in the thickness direction.

[Claim 11] The diffraction grating element according to claim 7 or 10, wherein the impurity is any element among Ge, P and B.

5 [Claim 12] The diffraction grating element according to claim 8, wherein the impurity is the element Ti.

[Claim 13] The diffraction grating element according to claim 9 or 10, wherein the first surface of the transparent flat plate is made of silica glass.

10 [Claim 14] The diffraction grating element according to claim 9 or 10, wherein the distribution of material in the thickness direction of the transparent flat plate is symmetrical.

15 [Claim 15] The diffraction grating element according to claim 14, wherein the diffraction grating is formed in the center in the thickness direction of the transparent flat plate.

20 [Claim 16] The diffraction grating element according to any one of claims 1, 3, 4, 5, and 6, wherein a diffraction efficiency is substantially polarization-independent.

[Detailed Description of the Invention]

[0001]

[Technical Field to which the Invention Pertains]

25 The present invention relates to a diffraction grating element in which a diffraction grating is provided on one

side of a transparent flat plate.

[0002]

[Prior Art]

5 A diffraction grating element generally has a
diffraction grating formed on a first surface of a
transparent flat plate that comprises the first surface and
a second surface that are parallel with one another (see
Non-Patent Literature 1, for example). In this diffraction
grating element, when, for example, light enters the first
10 surface from a medium that is in contact with the first
surface at a constant angle of incidence, this light is
diffracted by the diffraction grating formed on the first
surface, transmitted within the transparent flat plate, and
then emitted to the medium in contact with the second
15 surface. The diffraction angle of the light emitted from
the second surface of the transparent flat plate varies
according to the wavelength.

[0003]

20 Therefore, the diffraction grating element can be used
as an optical demultiplexer that demultiplexes incident
light and emits the demultiplexed light. Further, when the
light is guided in the opposite direction to this case, this
diffraction grating element can be used as an optical
multiplexer that multiplexes the incident light and emits
25 the multiplexed light. In addition, by combining the
diffraction grating element with other optical elements, a

dispersion regulator that regulates the group delay time of the light in accordance with the wavelength can also be constituted, for example. Therefore, the diffraction grating element is one important optical device in a wavelength division multiplexing (WDM) optical communication system that multiplexes multiple wavelength signal light and then transmits this multiplexed light.

[0004]

[Non-patent Literature 1]

Kashiko Kodate, "Development of diffractive optics and future challenges"; Japan Women's University Journal, Faculty of Science, 10th Edition, pages 7 to 24 (2002).

[0005]

[Problem to be Solved by the Invention]

However, even if the wavelength and angle of incidence of the light entering the diffraction grating element are constant, the diffraction angle varies according to the temperature. In a case where the diffraction grating element is used in a WDM optical communication system, when the diffraction angle of the diffraction grating element changes, the loss of signal light is therefore large or the waveform of the signal light deteriorates, and hence a communication error sometimes occurs. In order to suppress this communication error, conventionally, there has been a need to provide an active temperature control mechanism that keeps the temperature of the diffraction grating element

constant. However, the provision of the temperature control mechanism provokes an increase in the system costs and a system cost increase is also provoked due to the need for a supply of electrical power to the temperature control mechanism.

[0006]

The present invention has been accomplished in order to solve the above problem, and an object of the present invention is to provide a diffraction grating element that allows the temperature control mechanism to be dispensed with or simplified.

[0007]

[Means for Solving the Problem]

A diffraction grating element according to the present invention is characterized in that: in a transparent flat plate having a first surface and a second surface that are parallel with one another and are in contact with a medium, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface; and at any temperature within a temperature range -20°C to +80°C, a linear expansion coefficient of a period of the diffraction grating, and a temperature coefficient of a refractive index of the medium is 0. When the diffraction grating element is used in the typical environment temperature range from -20°C to +80°C of an optical communication system, the temperature control mechanism can.

be dispensed with or simplified. Preferably, in the diffraction grating element of the present invention, the medium is air, and the linear expansion coefficient of the period of the diffraction grating is from $0.63 \times 10^{-6}/K$ to $1.23 \times 10^{-6}/K$. In this case, at any temperature within the temperature range from $-20^{\circ}C$ to $+80^{\circ}C$ under atmospheric pressure, the sum of the linear expansion coefficient of the period of the diffraction grating and the temperature coefficient of the refractive index of the medium is 0.

10 [0008]

A diffraction grating element according to the present invention is characterized in that: in a transparent flat plate having a first surface and a second surface that are parallel with one another and are in contact with a medium, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface; the medium is air; and a linear expansion coefficient of a period of the diffraction grating is from $0.65 \times 10^{-6}/K$ to $1.11 \times 10^{-6}/K$. In this case, the maximum wavelength shift in the temperature range from $-20^{\circ}C$ to $+80^{\circ}C$ under atmospheric pressure is 0.04 nm or less. Therefore, the diffraction grating element can be suitably used in a WDM optical communication system in which the optical frequency interval of multiple wavelength signal light is 100 GHz.

25 [0009]

A diffraction grating element according to the present invention is characterized in that: in a transparent flat plate having a first surface and a second surface that are parallel with one another, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface; the transparent flat plate is disposed in a hermetically sealed gas or in a vacuum; and a linear expansion coefficient of a period of the diffraction grating is $2.4 \times 10^{-7}/K$ or less. In this diffraction grating element, the maximum wavelength shift when the diffraction grating element is hermetically sealed or in a vacuum in the temperature range from $-20^{\circ}C$ to $+80^{\circ}C$ is 0.04 nm or less. Therefore, the diffraction grating element can be suitably used in a WDM optical communication system in which the optical frequency interval of multiple wavelength signal light is 100 GHz.

[0010]

A diffraction grating element according to the present invention is characterized in that: in a transparent flat plate having a first surface and a second surface that are parallel with one another and are in contact with a medium, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface; the medium is air; and a linear expansion coefficient of a period of the diffraction grating is from $0.80 \times 10^{-6}/K$ to $0.95 \times 10^{-6}/K$. In this case, the maximum

wavelength shift in the temperature range from -20°C to $+80^{\circ}\text{C}$ under atmospheric pressure is 0.02 nm or less. Therefore, the diffraction grating element can be suitably used in a WDM optical communication system in which the optical frequency interval of multiple wavelength signal light is 50 GHz.

[0011]

A diffraction grating element according to the present invention is characterized in that: in a transparent flat plate having a first surface and a second surface that are parallel with one another, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface; the transparent flat plate is disposed in a hermetically sealed gas or in a vacuum; and a linear expansion coefficient of a period of the diffraction grating is $1.2 \times 10^{-7}/\text{K}$ or less. In this diffraction grating element, the maximum wavelength shift when the diffraction grating element is hermetically sealed or in a vacuum in the temperature range from -20°C to $+80^{\circ}\text{C}$ is 0.02 nm or less. Therefore, the diffraction grating element can be suitably used in a WDM optical communication system in which the optical frequency interval of multiple wavelength signal light is 50 GHz.

[0012]

In the diffraction grating element according to the present invention, the transparent flat plate could also

preferably be made of silica glass to which an impurity has been added. The transparent flat plate could also preferably be made of silica glass or crystallized glass to which an impurity has been added. The transparent flat plate could also preferably be constituted by laminating a plurality of optical glasses with different linear expansion coefficients. Alternatively, the transparent flat plate could also preferably be made of silica glass to which an impurity has been added at a different concentration in the thickness direction.

[0013]

In the case where an impurity is added to the transparent flat plate, the impurity is preferably any element among Ge, P, and B. Alternatively, the impurity is also preferably element Ti. For example, by adding an impurity of an appropriate concentration by means of VAD or CVD, or the like, the linear expansion coefficient of the diffraction grating formed on the transparent flat plate can be afforded the desired value. The section of the transparent flat plate where the diffraction grating is formed preferably is made of silica glass, and, in this case, the workability when forming the diffraction grating is highly superior.

[0014]

In the diffraction grating element according to the present invention, the distribution of the linear expansion

coefficient in the thickness direction of the transparent flat plate is preferably symmetrical. In this case, the occurrence of warp of the transparent flat plate is suppressed even in the event of a temperature change. In addition, the diffraction grating is preferably formed in the center in the thickness direction of the transparent flat plate. Here, the temperature dependence of the light emission position is also reduced.

[0015]

In the diffraction grating element according to the present invention, the diffraction efficiency is preferably substantially polarization-independent. In this case, even when the polarization state of the incident light is not constant, the incident light can be diffracted with constant diffraction efficiency without using other optical elements as required conventionally (polarization separation element, polarization composing element, and so forth).

[0016]

[Embodiments of the Invention]

Referring to the attached drawings, embodiments of the present invention will be described in detail below with. The same reference symbols have been assigned to the same elements or parts in the description of the drawings, and hence repetitive description is omitted here. Further, a xyz Cartesian coordinate system is sometimes shown in the drawings in order to facilitate the description.

[0017]

Fig. 1 is a sectional view of the diffraction grating element 1 relating to this embodiment. The diffraction grating element 1 shown in this figure is a diffraction grating element in which, in a transparent flat plate 10 that comprises a first surface 10A and a second surface 10B that are substantially parallel with one another and are in contact with a medium 21 and a medium 22 respectively. The grating direction of the diffraction grating formed in the first surface 10A is parallel with the y axis direction, and a recess and protrusion are cyclically formed at a period Λ in the x axis direction. In addition, a reflection reduction film is suitably provided on the second surface 10B. In this case, the diffraction efficiency is highly superior. Further, although medium 21 and 22 are air, for example, these media are not limited to air. Further, the transparent flat plate 10 consists of silica glass, for example, but need not be silica glass.

[0018]

In this diffraction grating element 1, light enters the first surface 10A of the transparent flat plate from via the medium 21. The incident plane is parallel with the plane xz. The light is diffracted by the diffraction grating formed in the first surface 10A, is transmitted within the transparent flat plate 10, and then emitted to the medium 22 in contact with the second surface 10B.

[0019]

The diffraction angle θ_m of the m-order diffracted light emitted by the second surface 10B of the transparent flat plate 10 is expressed by means of the following expression.

[0020]

[expression 1]

$$\theta_m = \sin^{-1} \left(\sin \theta + \frac{m\lambda}{n\Lambda} \right) \quad \dots (1)$$

Here, θ is the angle of incidence, λ is the wavelength of light in a vacuum, and n is the refractive index of the medium 21, 22. As may be understood from this equation, the diffraction angle θ_m is dependent on the wavelength λ and hence the diffraction grating element 1 is used as an optical demultiplexer or optical multiplexer, for example, or can also be used as one component of a dispersion regulator.

[0021]

Further, when the temperature T changes, the following problems arise. Fig. 2 illustrates a problem confronted by diffraction grating elements. Generally, the refractive index n of the medium 21 and 22 is a function of the temperature T , and the period Λ of the diffraction grating is also a function of the temperature T , and the diffraction angle θ_m therefore varies according to the temperature T .

If, as shown in Fig. 2, the incident light contains the wavelength components λ_1 to λ_3 , supposing that the optical system is regulated such that a component of wavelength λ_2 in the diffracted light excluding the 0 order diffracted light is received by an optical element 30 (photo diode, mirror, and so forth, for example), when the diffraction angle θ_m changes according to the change of temperature T , the wavelength of the light entering the optical element 30 shifts. Therefore, conventionally, there has been a need to provide an active temperature control mechanism that keeps the temperature of the diffraction grating element constant.

[0022]

The diffraction grating element 1 of this embodiment is capable of resolving this problem. That is, when the product $(n\Lambda)$, which is the temperature dependent component on the right side of Equation (1) above, is derived at temperature T , the following expression is obtained.

[0023]

[expression 2]

$$\frac{d(n\Lambda)}{dT} = n\Lambda \left(\frac{1}{n} \frac{dn}{dT} + \frac{1}{\Lambda} \frac{d\Lambda}{dT} \right) \quad \dots (2)$$

If the right side of Equation (2) is 0, the product $(n\Lambda)$ is constant and not dependent on the temperature T . Therefore, the diffraction angle θ_m is constant and not dependent on the temperature T .

[0024]

Here, the second item in the brackets on the right side of Equation (2) above is the linear expansion coefficient α of the period Λ of the diffraction grating that is represented by the following expression.

[0025]

[expression 3]

$$\alpha = \frac{1}{\Lambda} \frac{d\Lambda}{dT} \quad \dots (3)$$

Further, the first item in brackets on the right side of Equation (2) above is the temperature coefficient β for the refractive index n of the medium 21, 22 that is represented by the following equation.

[0026]

[expression 4]

$$\beta = \frac{1}{n} \frac{dn}{dT} \quad \dots (4)$$

Therefore, if the sum of the linear expansion coefficient α of the period Λ of the diffraction grating and the temperature coefficient β of the refractive index n of the medium 21, 22 is 0, that is, if the following relational expression is established, the diffraction angle θ_m is constant and not dependent on the temperature T .

[0027]

[expression 5]

$$\alpha + \beta = 0 \quad \dots (5)$$

[0028]

5 In the diffraction grating element 1 of this embodiment, at any temperature within the temperature range from -20°C to +80°C, the sum of the linear expansion coefficient α of the period Λ of the diffraction grating and the temperature coefficient β of the refractive index n of the medium 21 and 22 is 0. As a result, when the
10 diffraction grating element 1 is used in the typical environment temperature range -20°C to +80°C in an optical communication system, the temperature control mechanism can be dispensed with or simplified.

[0029]

15 A case where the medium 21 and 22 are air will be described below. Fig. 3 is a graph that shows the relationship between the temperature T and the temperature coefficient β of the refractive index n of air under atmospheric pressure. As shown in this figure, the
20 dependence of the refractive index n of air on the temperature T is small and is almost equal to the value 1. However, the temperature coefficient β of the refractive index n of air varies with a large dependence on the temperature T . Further, if the linear expansion coefficient

α (unit: 1/K) of the period Λ of the diffraction grating is within the following numerical value range:

[0030]

[expression 6]

$$0.63 \times 10^{-6} < \alpha < 1.23 \times 10^{-6} \quad \dots (6)$$

5

the relation of Equation (5) above is established at any temperature within the temperature range from -20°C to $+80^{\circ}\text{C}$ under atmospheric pressure. Further, if the linear expansion coefficient α of the period Λ of the diffraction grating is $0.89 \times 10^{-6}/\text{K}$, the relation of Equation (5) above is established at close to 25°C under atmospheric pressure, which is the ordinary usage temperature.

[0031]

Further, as described by using Fig. 2, generally, when the temperature T changes, the wavelength of the diffracted light entering the optical element 30 undergoes a shift. Fig. 4 is a graph showing the relationship between the maximum wavelength shift in the temperature range from -20°C to $+80^{\circ}\text{C}$ and the linear expansion coefficient α of the period Λ of the diffraction grating. This figure illustrates a case where the wavelength λ is $1.3 \mu\text{m}$, $1.5 \mu\text{m}$, and $1.7 \mu\text{m}$ respectively. Note that, in a WDM optical communication system, the wavelength band equal to or less than the wavelength $1.7 \mu\text{m}$ is generally used as the signal

light wavelength band.

[0032]

In cases where the optical frequency interval of multiple wavelength signal light in a WDM optical communication system is 100 GHz, the maximum wavelength shift in the temperature range from -20°C to +80°C under atmospheric pressure must be 0.04 nm or less. Therefore, according to Fig. 4, the linear expansion coefficient α (unit: 1/K) of the period Λ of the diffraction grating may fall in the following numerical value range.

[0033]

[expression 7]

$$0.65 \times 10^{-6} < \alpha < 1.11 \times 10^{-6} \quad \dots (7)$$

In addition, in cases where the optical frequency interval of the multiple wavelength signal light is 50 GHz, the maximum wavelength shift in the temperature range from -20°C to +80°C under atmospheric pressure must be 0.02 nm or less. Therefore, the linear expansion coefficient α (unit: 1/K) of period Λ of the diffraction grating may fall in the following numerical value range.

[0034]

[expression 8]

$$0.80 \times 10^{-6} < \alpha < 0.95 \times 10^{-6} \quad \dots (8)$$

[0035]

As described above, because the linear expansion coefficient α of the period Λ of the diffraction grating is in a suitable range, the diffraction grating element 1 relating to this embodiment is able to fulfill the accuracy required for WDM optical communications in the temperature range from -20°C to $+80^{\circ}\text{C}$, and hence the temperature control mechanism can be dispensed with or simplified. Note that the required accuracy varies according to the wavelength band for multiple wavelength signal light and the optical frequency interval.

[0036]

In the following, a method for implementing the desired value of the linear expansion coefficient α of the period Λ of the diffraction grating will be described. As a first method, an impurity (Ge, P, and B, or the like) may be added to silica glass to form the transparent flat plate 10. The linear expansion coefficient of silica glass is $0.5 \times 10^{-6}/\text{K}$, and that is outside the numerical value range above. However, by appropriately setting the addition concentration of the impurity added to the silica glass, it is possible to implement the desired value for the linear expansion coefficient of the silica glass.

[0037]

For example, when the impurity added to the silica glass is Ge, the linear expansion coefficient α (unit: 1/K) of the silica glass is expressed, given a Ge addition concentration M_{Ge} (unit: mol%), by the following relational expression.

[0038]

[expression 9]

$$\alpha = 0.5 \times 10^{-6} + 0.076 \times 10^{-6} M_{Ge} \quad \dots (9)$$

Therefore, in order to render the numerical value range of the linear expansion coefficient α expressed by Equation (6) above, the Ge addition concentration M_{Ge} may be from 1.7mol% to 9.6mol%. In addition, in order to render the numerical value range of the linear expansion coefficient α expressed by Equation (8) above, the Ge addition concentration M_{Ge} may be 3.9mol% to 5.9mol%.

[0039]

So too when another impurity (P, B, or the like) other than Ge is added, by appropriately setting the addition concentration, the desired value for the linear expansion coefficient of the silica glass can be implemented. Further, when the productivity of the transparent flat plate 10 is considered, a plurality of types of impurity is suitably added to the silica glass. Further, manufacture can be

performed by VAD or CVD, for example.

[0040]

As a second method for implementing the desired value for the linear expansion coefficient α of the period Λ of the diffraction grating, a plurality of optical glasses that have different linear expansion coefficients may be laminated to form the transparent flat plate 10. Fig. 5 is an explanatory view of another constitutional example of the diffraction grating element 1 relating to this embodiment. In the diffraction grating element 1 shown here, the transparent flat plate 10 is produced by sequentially laminating three optical glasses 11 to 13. The optical glass 11 is in contact with the medium 21 and the optical glass 13 is in contact with the medium 22, and the optical glass 12 is interposed between the optical glass 11 and the optical glass 13.

[0041]

Further, the linear expansion coefficient distribution in the thickness direction of the transparent flat plate 10 is suitably symmetrical. In this case, the occurrence of warp of the transparent flat plate 10 is suppressed even in the event of a temperature change. Supposing that the optical glasses 11 and 13 each have a thickness of $t1/2$, Young's modulus is $E1$, Poisson's ratio is $\nu1$, and the linear expansion coefficient is $\alpha1$. Let us suppose also that for the optical glass 12, the thickness is $t2$, Young's modulus

is E2, Poisson's ratio is ν_2 , and the linear expansion coefficient is α_2 . The linear expansion coefficient (that is, the linear expansion coefficient α of the period Λ of the diffraction grating) of the transparent flat plate 10 is then expressed by the following expression.

[0042]

[expression 10]

$$\alpha = \frac{\frac{E_1 t_1}{1 - \nu_1} \alpha_1 + \frac{E_2 t_2}{1 - \nu_2} \alpha_2}{\frac{E_1 t_1}{1 - \nu_1} + \frac{E_2 t_2}{1 - \nu_2}} \quad \dots (10)$$

Further, because the thickness of each of the optical glasses 11 to 13 is sufficiently large due to the thickness of the recesses and protrusions of the diffraction grating, the influence exerted by the recesses and protrusions of the diffraction grating can be disregarded.

[0043]

Further, the machinability of the optical glass 11 and the optical glass 13 for the formation of the diffraction grating is suitably highly superior. The physicality and thickness of the optical glass 12 are suitably set appropriately so that the linear expansion coefficient α of the period Λ of the diffraction grating is afforded the desired value in accordance with Equation (10) above. For example, the optical glass 11 and optical glass 13 suitably is made of silica glass. In addition, the optical glass 12 suitably made of silica glass to which Ge has been added as

an impurity.

[0044]

Fig. 6 is a graph showing the relationship between the linear expansion coefficients α of the period Λ of the diffraction grating, and the thickness ratio (t_2/t_1). Here, the impurity added to the optical glass 12 is Ge, and the addition concentration is set at 10mol% and 15mol% respectively. As may be seen from this figure, by suitably setting the impurity addition concentration and thickness of the optical glass 12, the linear expansion coefficient α of the period Λ of the diffraction grating can be afforded the desired value.

[0045]

Here, when the difference between the refractive index of the optical glasses 11 and 13 and the refractive index of the optical glass 12 is large, the reflection of light at the interface between these optical glasses is large and hence the diffraction efficiency is poor. Therefore, in order to suppress reflection at the interface, the refractive index difference is preferably smaller. When the optical glasses 11 and 13 are silica glass and the optical glass 12 is silica glass whose Ge addition concentration is 15mol%, the refractive index difference is extremely small at 0.022 and hence reflection at the interface is suppressed.

[0046]

An adhesive is used for the pasting together of the

optical glasses 11 to 13. The refractive index of this adhesive is preferably also close to the refractive index of the optical glasses 11 to 13. Anode bonding may also be used for the pasting together of the optical glasses 11 to 13. In this case, adhesive is unnecessary and hence there is no influence exerted by the linear expansion of the adhesive. Hence, anode bonding is also suitable in this respect.

[0047]

As a third method for implementing the desired value of the linear expansion coefficient α of the period Λ of the diffraction grating, the transparent flat plate 10 may be made of silica glass to which an impurity (Ge, P and B, and so forth) has been added in a different concentration in the thickness direction. Fig. 7 is an explanatory view of yet another constitutional example of the diffraction grating element 1 relating to this embodiment. This figure shows the addition concentration distribution of Ge in the thickness direction of the transparent flat plate 10. In the diffraction grating element 1 shown in this figure, the transparent flat plate 10 is silica glass in neighboring regions that include the first surface 10A and second surface 10B respectively and has Ge added as an impurity in a middle region. This transparent flat plate 10 is manufactured by means of VAD and CVD and so forth.

[0048]

In this case also, the linear expansion coefficient distribution is suitably symmetrical in the thickness direction of the transparent flat plate 10. In this diffraction grating element 1, the occurrence of warp of the transparent flat plate 10 is suppressed even in the event of a temperature change. The linear expansion coefficient of the transparent flat plate 10 (that is, the linear expansion coefficient α of the period Λ of the diffraction grating) is expressed by the following expression.

[0049]

[expression 11]

$$\alpha = \frac{\int_0^l \frac{E(z)}{1-\nu(z)} \alpha(z) dz}{\int_0^l \frac{E(z)}{1-\nu(z)} dz} \quad \dots(11)$$

Here, l is the thickness of the transparent flat plate 10 and the z coordinate value of the second surface 10B is 0.

[0050]

Neighboring regions that include the first surface 10A and the second surface 10B respectively are silica glass and hence the machinability is suitably highly superior in order to form the diffraction grating. By appropriately setting the impurity addition concentration and the thickness in accordance with Equation (11) above, the linear expansion coefficient α of the period Λ of the diffraction grating can be afforded the desired value. Further, by smoothly

changing the impurity addition concentration in the thickness direction, the refractive index can be changed smoothly in the thickness direction. As a result, the reflection of light in sections exhibiting a refractive index variation can be suppressed.

[0051]

As a fourth method for implementing the desired value of the linear expansion coefficient α of the period Λ of the diffraction grating, the diffraction grating may be formed by forming a film on one side of the transparent flat plate 10 and then performing etching. Figs. 8 and 9 are explanatory views of yet another constitutional example of the diffraction grating element 1 relating to this embodiment. In the diffraction grating element 1 which is shown in these figures, the transparent flat plate 10 is made of silica glass to which an impurity such as the element Ge or Ti, or the like, has been added, for example. The diffraction grating element 1 shown in Fig. 8 is a diffraction grating formed by the vapor deposition of a single-layer film 10a on one side of the transparent flat plate 10, and then etching by means of patterning to leave a film 10a on the period Λ pattern. The diffraction grating element 1 shown in Fig. 9 is a diffraction grating which is formed by the vapor deposition of multiple layer films 10a, 10b, and 10c on one side of the transparent flat plate 10, and then etching by means of patterning to leave films 10a,

10b on the period Λ pattern.

[0052]

In this diffraction grating element 1, the linear expansion coefficient α of the period Λ of the diffraction grating is afforded the desired value by appropriately adjusting the addition concentration of the impurity which has been added to the transparent flat plate 10. Further, in this case, even when etching of the transparent flat plate 10 is difficult, by appropriately selecting the material of the film formed on the one side, the diffraction grating can be formed easily. In addition, in the case of the diffraction grating element 1 shown in Fig. 9 in particular, the polarization dependence of the diffraction characteristic in a broad wavelength band can be reduced by appropriately selecting the refractive index of each of the films 10a, 10b, and 10c.

[0053]

In the description of the embodiments hereinabove, it was assumed that the diffraction grating element 1 was placed under atmospheric pressure and the medium 21 and 22 were gases at atmospheric pressure. However, there are cases where the diffraction grating element 1 is hermetically sealed in a package. In this case, a temperature change results in a change in the gas pressure, and the refractive index of the gas changes as a result of this change in pressure. A case where the diffraction

grating element 1 is hermetically sealed will be described below.

[0054]

The diffraction grating element 1 relating to this
5 embodiment is used, not only as an optical demultiplexer or
optical multiplexer, but also suitably in a WDM optical
communication system as a component of an optical module
such as a dispersion regulator, spectral detector and an
optical filter. Further, in these optical modules, the
10 diffraction grating element 1 is sometimes provided in a
package together with semiconductor parts such as a laser
diode, photodiode, and a MEMS (Micro Electro Mechanical
System). Further, generally speaking, the semiconductor
parts are hermetically sealed in order to prevent
15 degradation caused by the effects of hydrogen and water
vapor. Further, also in the case of the optical modules not
including semiconductor parts, by suppressing the adhesion
of foreign matter to the diffraction grating element 1 by
means of hermetic sealing, favorable characteristics can be
20 maintained. A concrete example where the temperature
dependence of the diffraction characteristic is reduced by
means of hermetic sealing is illustrated below.

[0055]

The refractive index n of gas is generally expressed
25 by the following expression.

[0056]

[expression 12]

$$n = 1 + \Delta n \quad \dots (12)$$

Here, Δn expresses the difference with respect to the refractive index of a vacuum. Δn varies according to the gas.

5 The values of He, Ne, Ar and N₂ at one atmosphere when the temperature is 0°C are:

[0057]

[expression 13]

$$\text{He} \quad \Delta n = 0.35 \times 10^{-4} \quad \dots (13a)$$

$$\text{Ne} \quad \Delta n = 0.67 \times 10^{-4} \quad \dots (13b)$$

$$\text{Ar} \quad \Delta n = 2.84 \times 10^{-4} \quad \dots (13c)$$

$$\text{N}_2 \quad \Delta n = 2.97 \times 10^{-4} \quad \dots (13d)$$

10 [0058]

When the temperature or pressure changes, Δn varies substantially in proportion to the gas density. Supposing that the gas density in the event of a hermetic seal is ρ_0 , the gas temperature in the event of a hermetic seal is T_0 ,
15 and the cubic expansion coefficient of the gas is γ . Here, the refractive index n of the gas at the temperature T is expressed by the following expression.

[0059]

[expression 14]

$$n = 1 + \Delta n \frac{\rho}{\rho_0} \quad \dots (14)$$

The density ρ of the gas at temperature T is expressed by the following expression.

[0060]

5 [expression 15]

$$\frac{\rho}{\rho_0} = 1 - \gamma(T - T_0) \quad \dots (15)$$

Accordingly, the temperature coefficient β of the refractive index of the gas in the event of a hermetic seal is expressed by the following expression.

10 [0061]

[expression 16]

$$\beta = -\Delta n \gamma \quad \dots (16)$$

[0062]

15 When the material of the package that houses and seals the diffraction grating element 1 (and the semiconductor parts) is Al (aluminum), the linear expansion coefficient of the package is $23 \times 10^{-6}/^{\circ}\text{C}$, and hence the cubic expansion coefficient γ of the gas within the package is $69 \times 10^{-6}/^{\circ}\text{C}$ ($= 3 \times 23 \times 10^{-6}$). Accordingly, when the gas is He, the
20 temperature coefficient β of the refractive index of the gas in the event of a hermetic seal is $-0.024 \times 10^{-7}/^{\circ}\text{C}$, and is -

$0.20 \times 10^{-7}/^{\circ}\text{C}$ for N_2 gas.

[0063]

The absolute value of this value of the temperature coefficient β of the refractive index of the gas in the event of a hermetic seal is also one or more digits smaller than the linear expansion coefficient $5 \times 10^{-7}/^{\circ}\text{C}$ of silica glass. Further, at atmospheric pressure, the cubic expansion coefficient of the gas is inversely proportional to the absolute temperature and is $3.7 \times 10^{-3}/^{\circ}\text{C}$ ($=1/273$) at a temperature of 0°C , for example. Therefore, the absolute value of the cubic expansion coefficient γ of the gas that is hermetically sealed by means of an Al package is also two or more digits smaller than the cubic expansion coefficient of the gas at atmospheric pressure.

[0064]

In comparison with a case where the diffraction grating element 1 is placed under atmospheric pressure, in a case where the diffraction grating element 1 is hermetically sealed in this manner, the temperature coefficient β of the refractive index n of the gas (medium 21 and 22) is small and the temperature dependence of the temperature coefficient β is also small, and hence the suitable range for the linear expansion coefficient α of the period Λ of the diffraction grating varies.

[0065]

In a case where the diffraction grating element 1 is

used in a WDM optical communication system without temperature adjustment, when the optical frequency interval of the multiple wavelength signal light is 100 GHz, the wavelength shift of the diffraction grating for each unit temperature change is desirably 0.4 pm/°C or less (the wavelength shift in the temperature range from -20°C to +80°C is equal to or less than 0.04 nm). Further, when the optical frequency interval of the multiple wavelength signal light is 50 GHz, the wavelength shift of the diffraction grating for each unit temperature change is desirably 0.2 pm/°C or less (the wavelength shift in the temperature range from -20°C to +80°C is equal to or less than 0.02 nm). Note that the required accuracy varies according to the wavelength band and optical frequency interval, and so forth, of the multiple wavelength signal light.

[0066]

Here, the wavelength shift of the diffraction grating for each unit temperature change is expressed by the following expression.

[0067]

[expression 17]

$$\frac{d\lambda}{dT} = \lambda(\alpha + \beta) \quad \dots (17)$$

[0068]

The wavelength of the signal light that is generally

used in WDM optical communication is $1.7 \mu\text{m}$ or less, and hence, in order that the wavelength shift of the whole range of the signal light wavelength band should be $0.4 \text{ pm}/^\circ\text{C}$ or less (or $0.2 \text{ pm}/^\circ\text{C}$ or less), the following conditions may be

5 satisfied.

[0069]

[expression 18]

$$|\alpha + \beta| \leq 0.4[\text{pm}/^\circ\text{C}] / 1.7[\mu\text{m}] = 2.4 \times 10^{-7} [^\circ\text{C}] \quad \dots (18a)$$

$$|\alpha + \beta| \leq 0.2[\text{pm}/^\circ\text{C}] / 1.7[\mu\text{m}] = 1.2 \times 10^{-7} [^\circ\text{C}] \quad \dots (18b)$$

[0070]

10 The value on the right side of Equation (18) above is approximately one digit larger than the temperature coefficient β of the refractive index n of the gas when the diffraction grating element 1 is hermetically sealed. So too when using an package made of a material with a large

15 linear expansion coefficient such as Al (aluminum), if the diffraction grating element 1 is hermetically sealed in this package, the temperature coefficient β of the refractive index n of the gas (medium 21 and 22) can be disregarded. Therefore, also inclusive of a case where the interior of

20 the package is at a vacuum, the linear expansion coefficient α of the period Λ of the diffraction grating may satisfy the following conditions when the optical frequency interval is 100 GHz and 50 GHz respectively.

[0071]

[expression 19]

$$|\alpha| \leq 2.4 \times 10^{-7} / ^\circ\text{C} \quad \dots (19a)$$

$$|\alpha| \leq 1.2 \times 10^{-7} / ^\circ\text{C} \quad \dots (19b)$$

Further, even in the event of sealing, when the linear expansion coefficient is large as is the case when the material of the sealing package is resin, Equations (18a) and (18b) above must be satisfied by considering the temperature coefficient β of the refractive index of the gas when the diffraction grating element 1 is hermetically sealed.

[0072]

In a case where the diffraction grating element 1 is hermetically sealed, the linear expansion coefficient α of the period Λ of the diffraction grating must be smaller than the linear expansion coefficient ($5 \times 10^{-7} / ^\circ\text{C}$) of the silica glass. In order to achieve this, crystallized glass is suitably used for the transparent flat plate 10. Alternatively, silica glass to which the element Ti has been added is suitably used for the transparent flat plate 10. By adjusting the degree of crystallization when crystallized glass is used and adjusting the amount of Ti added in the case of silica glass to which the element Ti is added, the linear expansion coefficient can be afforded a value in the range from $-20 \times 10^{-7} / ^\circ\text{C}$ to $+5 \times 10^{-7} / ^\circ\text{C}$, for example. Further, glass which exhibits substantially no thermal expansion is

suitably used for the transparent flat plate 10. Further, in the constitution shown in Fig. 5, silica glass may be used for the optical glasses 11 and 13 and glass with a negative linear expansion coefficient may be used for the optical glass 12.

[0073]

The diffraction grating element 1 of the embodiments hereinabove had a diffraction grating formed in or above one surface of the transparent flat plate 10. However, a diffraction grating may be formed internally so as to lie substantially in parallel with the surface of the transparent flat plate. A diffraction grating element in which the diffraction grating is formed within the transparent flat plate will be described below.

[0074]

Fig. 10 is a sectional view of a diffraction grating element 2 relating to this embodiment. The diffraction grating element 2 shown in this figure is one in which a diffraction grating 10a is formed within a transparent flat plate 10, which has a first surface 10A and a second surface 10B that are in parallel with one another and in contact with the medium 21 and 22 respectively, in parallel with the first surface 10A. The transparent flat plate 10 is silica glass to which the element Ge or Ti, for example, has been added. The diffraction grating 10a is formed at the center in the thickness direction (z axis direction) of the

transparent flat plate 10, is a vertically symmetrical structure, and is formed cyclically at the period Λ in the x axis direction with the grating direction parallel with the y axis. In addition, a reflection reduction film is suitably provided on the first surface 10A and the second surface 10B. So too in the case of the diffraction grating element 2, the linear expansion coefficient α of the period Λ of the diffraction grating satisfies any of Equations (5) to (8) above when the diffraction grating element is placed under atmospheric pressure, or satisfies Equation (18a) or (18b) above when the diffraction grating element is hermetically sealed. The temperature dependence of the diffraction angle of the diffraction grating element 2 is reduced in the same way as the diffraction grating element 1 mentioned earlier in which the diffraction grating is formed in or above the first surface 10A.

[0075]

In addition, when the diffraction grating element 2 is used under the Bragg condition whereby a high diffraction efficiency is generally obtained, the temperature dependence of the position at which the light is emitted from the second surface 10B is also suppressed. That is, supposing that the angle of incidence of the light from the medium 21 to the first surface 10A is θ , the wavelength of this light is λ , the period of the diffraction grating is Λ , and the refractive index of the medium 21 and 22 is n , the Bragg

condition for the m-order diffracted light is expressed by the following expression.

[0076]

[expression 20]

$$\sin \theta = -\frac{m\lambda}{2n\Lambda} \quad \dots (20)$$

5

Under the Bragg condition, the angle of incidence and diffraction angle have equal absolute values of the opposite sign. Further, the diffraction grating 10a is formed in the center in the thickness direction (z axis direction) of the transparent flat plate 10 to produce a vertically symmetrical structure. Therefore, in the x axis direction, the position at which the light emits via the second surface 10B is equal to the position at which the light enters the first surface 10A. Supposing that the temperature dependence of the product (n Λ) in Equation (20) above no longer exists, because there is no temperature dependence of the position at which the light enters the first surface 10A, the Bragg condition is always satisfied irrespective of the temperature and there is therefore no longer any temperature dependence of the position at which the light emits via the second surface 10B. Therefore, if the temperature dependence of the product (n Λ) constituting the temperature dependence component in Equation (20) above is reduced, not only is it possible to diminish the temperature dependence

10

15

20

of the diffraction angle, the temperature dependence of the emitting position can also be reduced.

[0077]

Fig. 11 is a sectional view of a diffraction grating element 3 according to the embodiment. The diffraction grating element 3 shown in this figure is a modified example of the diffraction grating element 2 mentioned earlier, the transparent flat plate 10 thereof being constituted by sequentially laminating the three optical glasses 11 to 13. The three optical glasses 11 to 13 of the diffraction grating element 3 are similar to the constitution shown in Fig. 5. The optical glass 12 at the center is silica glass, for example, and the optical glasses 11 and 13 on either side thereof are each made of silica glass to which the element Ge or Ti, for example, has been added. The diffraction grating 10a is formed at the center in the thickness direction (z axis direction) of the central optical glass 12, is a vertically symmetrical structure, and is formed cyclically at the period Λ in the x axis direction with the grating direction parallel with the y axis. In addition, a reflection reduction film is suitably provided on the surface of the optical glasses 11 and 13 respectively. So too in the case of the diffraction grating element 3, the linear expansion coefficient α of the period Λ of the diffraction grating satisfies any of Equations (5) to (8) above when the diffraction grating element is placed under

atmospheric pressure, or satisfies Equation (18a) or (18b) above when the diffraction grating element is hermetically sealed. Similarly to the diffraction grating element 2 mentioned earlier, with the diffraction grating element 3, if the temperature dependence of the product $(n\Lambda)$ is diminished, the temperature dependence of the diffraction angle is reduced and the temperature of the emitting position is also reduced.

[0078]

The diffraction grating elements 2 and 3 are produced as detailed below. Another transparent glass that is smooth on both surfaces is pasted onto the diffraction grating surface of transparent glass in whose surface the diffraction grating is formed by etching or similar. The transparent flat plate 10 of the diffraction grating element 2 or the optical glass 12 of the diffraction grating element 3 is glued together. Alternatively, the surface of the diffraction grating surface of the transparent glass in which the diffraction grating is formed by etching or similar has a grating groove that is embedded by means of a high refractive index material such as TiO_2 , Ta_2O_5 , or Nb_2O_5 by means of vapor deposition and then another transparent glass that is smooth on both surfaces is pasted onto the diffraction grating side. The transparent flat plate 10 of the diffraction grating element 2 or the optical glass 12 of the diffraction grating element 3 may be glued together. In

the latter case, because the whole of the diffraction grating side is solid, the pasting work is straightforward. Further, in the latter case, when a surface treatment such as grinding is performed after the embedding by means of a high refractive index material, the pasting work is even easier and hence suitable.

[0079]

Fig. 12 is a sectional view of a diffraction grating element 4 according to this embodiment. In the diffraction grating element 4 shown in this figure, the transparent flat plate 10 has a diffraction grating that is formed in a region interposed between the optical glass 11 and the optical glass 12. This diffraction grating is constituted such that a medium 14a and a medium 14b are provided alternately at the period Λ in the x axis direction.

[0080]

In addition, Fig. 13 is a sectional view of a diffraction grating element 5 relating to this embodiment. In the diffraction grating element 5 shown in this figure, the transparent flat plate 10 comprises films 15 to 18 that are sequentially formed in regions that are interposed between the optical glass 11 and the optical glass 12, and comprises a diffraction grating that is formed between the films 16 and 17. This diffraction grating is constituted such that the medium 14a and 14b are provided alternately at the period Λ in the x axis direction.

[0081]

So too with these diffraction grating elements 4 and 5, the linear expansion coefficient α of the period Λ of the diffraction grating satisfies any of Equations (5) to (8) above when the diffraction grating elements are placed under atmospheric pressure. Alternatively, the linear expansion coefficient α satisfies Equation (18a) or (18b) above when the diffraction grating elements are hermetically sealed. Similarly to the diffraction grating element 2 mentioned earlier, with these diffraction grating elements 4 and 5, if the temperature dependence of the product ($n\Lambda$) is diminished, the temperature dependence of the diffraction angle is reduced and the temperature dependence of the emitting position is also reduced.

[0082]

The diffraction efficiency of these diffraction grating elements 4 and 5 can also be improved in a broader wavelength band. Further, the polarization dependence of the diffraction grating elements 4 and 5 can be suppressed and, because there is therefore no need to provide a polarization separation element or polarization composing element, or the like, separately from the diffraction grating element, it is possible to remove the influence exerted by the temperature dependence of the polarization separation and composing of this polarization separation element or polarization composing element, or the like.

[0083]

Further, in the case of the diffraction grating element 5, in a normal case, because the films 15 to 18 and the medium 14a and 14b are adequately thin and hardly affect the linear expansion coefficient of the transparent flat plate 10, these parts need not be vertically symmetrical.

[0084]

A description was provided above for the suppression of the temperature dependence of a diffraction grating element unit. Incidentally, generally speaking, the diffraction grating element is sometimes used together with other optical elements. For example, when the polarization state of the incident light is not constant, the diffraction grating element is used together with a polarization separation element, a polarization rotation element and a polarization composing element. In this case, the incident light is polarization-separated by the polarization separation element to produce two linear polarized light components whose polarization planes are orthogonal to one another. Of the light of the two linear polarized light components that have been polarization-separated, one polarization plane is rotated by the polarization rotation element through 90° to render linear polarized light with the same orientation, and then enters the diffraction grating element before being diffracted. Of the light of the two linear polarized light components that is diffracted

by the diffraction grating element, one polarization plane is rotated by another polarization rotation element through 90° to produce linear polarized light whose polarization planes are orthogonal to one another, and the light is then
5 subjected to polarization composing by the polarization composing element before being emitted.

[0085]

In such a case, in addition to the temperature dependence being suppressed in diffraction grating element,
10 the other optical elements (polarization separation element, polarization composing element, and the polarization rotation element) are generally also temperature-dependent and hence a temperature control mechanism is required. However, when the temperature control load is large for the
15 other optical elements, the significance of dispensing with or simplifying the temperature control mechanism is reduced for the diffraction grating element.

[0086]

Therefore, the diffraction grating element 1 relating
20 to this embodiment is suitably a diffraction grating element whose temperature dependence is suppressed and in which the polarization dependence of the diffraction efficiency is also suppressed. Accordingly, even when the polarization state of the incident light is not constant, the incident
25 light can be diffracted with constant diffraction efficiency by the diffraction grating element 1 alone without using the

other optical elements mentioned above (the polarization separation element, the polarization composing element, and the polarization rotation element).

[0087]

5 For example, let us suppose that, as shown in Fig. 14, the cross-section of the diffraction grating has rectangular recesses and protrusions, that the period Λ is $1.55 \mu\text{m}$, the height H of the protruding strips is $3.72 \mu\text{m}$, and the ratio (W/Λ) between the width W of the protruding strips and the
10 period Λ is 0.66. Suppose that the transparent flat plate 10 consists of silica glass and that the medium 21 and 22 are air. Further, let us assume that a non-reflective coating is formed on the second surface 10B of the transparent flat plate 10. Here, supposing that the
15 wavelength of the light entering the first surface 10A from the medium 21 is $1.55 \mu\text{m}$ and the angle of incidence θ is 30° , the diffraction efficiency of the TE polarized light and the TM polarized light is then on the order of 98% and the diffraction efficiency is substantially polarization-
20 independent.

[0088]

[Effects of the Invention]

As explained above, a diffraction grating element according to the present invention is characterized that: in
25 a transparent flat plate having a first surface and a second surface which are parallel with one another and are in

contact with a medium, a diffraction grating is provided on the first surface or within the transparent flat plate in parallel with the first surface; and at any temperature within a temperature range -20°C to $+80^{\circ}\text{C}$, a linear expansion coefficient of a period of the diffraction grating, and a temperature coefficient of a refractive index of the medium is 0. When the diffraction grating element is used in the typical environment temperature range from -20°C to $+80^{\circ}\text{C}$ of an optical communication system, the temperature control mechanism can be dispensed with or simplified.

[Brief Description of the Drawings]

[Fig. 1]

Fig. 1 is a sectional view of a diffraction grating element 1 relating to the embodiment.

[Fig. 2]

Fig. 2 illustrates a problem confronted by diffraction grating elements.

[Fig. 3]

Fig. 3 is a graph that shows the relationship between the temperature T and the temperature coefficient of the refractive index n of air.

[Fig. 4]

Fig. 4 is a graph showing the relationship between the maximum wavelength shift in the temperature range from -20°C to $+80^{\circ}\text{C}$ and the linear expansion coefficient α of the period Λ of the diffraction grating.

[Fig. 5]

Fig. 5 is an explanatory view of another constitutional example of the diffraction grating element 1 relating to the embodiment.

5 [Fig. 6]

Fig. 6 is a graph showing the relationship between the linear expansion coefficients α of the period Λ of the diffraction grating and the thickness ratio (t_2/t_1).

[Fig. 7]

10 Fig. 7 is an explanatory view of yet another constitutional example of the diffraction grating element 1 relating to the embodiment.

[Fig. 8]

15 Fig. 8 is an explanatory view of yet another constitutional example of the diffraction grating element 1 relating to the embodiment.

[Fig. 8]

20 Fig. 9 is an explanatory view of yet another constitutional example of the diffraction grating element 1 relating to the embodiment.

[Fig. 10]

Fig. 10 is a sectional view of a diffraction grating element 2 relating to the embodiment.

[Fig. 11]

25 Fig. 11 is a sectional view of a diffraction grating element 3 relating to the embodiment.

[Fig. 12]

Fig. 12 is a sectional view of a diffraction grating element 4 relating to the embodiment.

[Fig. 13]

5 Fig. 13 is a sectional view of a diffraction grating element 5 relating to the embodiment.

[Fig. 14]

10 Fig. 14 illustrates a method of implementing the polarization independence of the diffraction grating element 1 relating to the embodiment.

[Explanation of Reference Numerals]

1-5: diffraction grating element

10: transparent flat plate

10A: first surface

15 10B: second surface

11-13: optical glass

21, 22: medium